

Cerastil® RW-3713 is a improved concentrate with the consistency of latex house paint. The vehicle dries by evaporation, leaving a high density, close-knit layer of graphite.

Cerastil® RW-3713 contains no metallic additives or impurities that will react with, or stick to, most metals or slags. It can be brushed, roller brushed, or diluted with water and sprayed on any surface.

is manufactured with a purity synthetic graphite to minimize trace elements. It can be brushed, roller brushed, sprayed on metal or graphite molds.

Unequalled for coating graphite trays and jigs where elimination of rough dimpled surfaces and sticking of Tungsten Carbide PM parts is necessary. This material can prevent the bonding of the migrating cobalt alloys. It can prevent the loss of structural support and sag. It leaves the parts with very smooth, pore-free, high-density surfaces

Technical Data:

UNCURED PROPERTIES:

Colour:	dunkel grau
Resin:	LT
Filler	ca. 23% Graphit
Specific gravity :	0,95 g/cm ³
ph-Value:	9

Unsere Merkblätter wurden nach bestem Wissen zusammen-gestellt. Die darin angegebenen Daten dienen ausschließlich zur Information des Benutzers und beschreiben keine rechtsverbindlichen Eigenschaften. Wir empfehlen, unsere Produkte darauf zu prüfen, ob sie dem jeweiligen Anwendungszweck des Benutzers genügen. Für eine weitergehende Beratung steht unsere Anwendungstechnische Abteilung zur Verfügung. Generell, auch bei Gewährleistungsansprüchen, gelten

CURED PROPERTIES:

Temperature rating:	-93 to 2000 °C
---------------------	----------------

Adhesives
and more...