



TECHNICAL DATASHEET

Penloc® FSS

Technical Data

Color	red
Resin	acrylat
Strength	Highstrength
max. Spiel:	0,55 mm

UNCURED PROPERTIES

Viscosity (Brookfield LVT/25°C) [Pa*s]	250000
Flash point [°C]	> 100

Curing

Handling Strength	5 - 20 min.
Functional Strength	45 - 300 min.
Full Strength	6 - 24 hour

CURED PROPERTIES

Temperature Resistance	-40 to 150 °C
Breakaway Torque	12,5 Nm
Prevailing Torque	13,5 Nm
Compression Shear Strength	10,5 N/mm ²
Dielectric Strength	8.5 kV/mm

Attention: Datasheet isn't decontrolled

Our data sheets have been compiled to the best of our knowledge. The information included in our data sheets is exclusive information for the intended user and describes characteristics, with no declaration of commitment. We recommend trials in order to confirm that our products satisfy the particular application requirements. For an additional technical consultation, please contact our R&D department. In general, for guarantee claims, please refer to our standard terms and conditions.

**Kleben
und mehr...**